



matting / athletics / flooring

## 3M™ NOMAD™ SCRAPER MATTING 6050 INSTALLATION

### CUSTOM CUTTING

3M™ Nomad™ Scraper Matting 6050 can be easily custom cut without edges fraying. Length and width dimensions may change during use. Wall-to-wall installations are not recommended.

#### Tools needed:

- Utility knife
- Straight edge, 3-4 feet (1-1.3 m) long
- If matting is to be cut to close specifications, be certain it is relaxed and not stretched. Unroll matting and allow to lie undisturbed for 24 hours at room temperature.
- Use a utility knife and straight edge for cutting. Do not use scissors.
- If it is necessary to move matting after cutting, roll it loosely to avoid stretching.

### SEAMING

3M™ Nomad™ Scraper Matting 6050 can be seamed together to make mats wider or longer than standard sizes.

#### Materials needed:

- 3M™ Matting Seaming Tape (kit or roll)
- 3M™ Matting Adhesive (one 3-ounce tube of adhesive will seam 15 linear feet [4.5 m] of matting)
- Before seaming, be certain that matting is relaxed and not stretched. Unroll matting and allow to lie undisturbed for 24 hours at room temperature. Avoid stretching or pulling on mat when seaming.
- Use pieces from the same roll to assure that color, shade and texture are the same.

- Maximum recommended mat size is 80 square feet (7.2 square meters).

You may want to use smaller mats for ease of handling and maintenance.

1. Place pieces of matting to be seamed side by side on a clean surface.
2. Unroll 3M™ Matting Seaming Tape between the two pieces of matting to be joined. Cut tape to length.
3. Position the pieces of matting on the seaming tape so that each piece's edge covers half the width of the tape. Be sure the pieces of matting touch at the tape center but do not overlap or buckle.
4. Fold back the edge of one piece of the matting along the full length of the seam.
5. When applying adhesive work rapidly. Adhesive may cause wrinkling of the seaming tape if the matting is not joined within 5 minutes of applying the adhesive. Apply adhesive in a continuous "zig-zag" pattern staying ¼ inch (6 mm) from the outside edge of the exposed half of the seaming tape.
6. Return the folded edge of the matting to its original position and apply moderate pressure to bond the adhesive.
7. Fold back the second piece of matting along the full seam length.
8. Apply two additional beads of adhesive, the first along the joint of the seaming tape and the first piece of matting, and the second in a wavy pattern ¼ inch (6 mm) from the outside edge of the exposed half of the seaming tape.
9. Return the folded back edge of the matting back into its original position and press firmly. At the same time,

gently push both pieces of matting together to eliminate any gaps.

10. Place a weight, such as a board, along the full length of the seam to maintain pressure on the bond. Allow to dry undisturbed for at least 8 hours before placing it into service.

## **APPLYING MAT EDGING**

Edging can be easily applied to 3M™ Nomad™ Scrapper Matting 6050 to form a tapered edge

### **Tools and Materials needed:**

- Utility knife
  - Straight edge, 3-4 feet (1-1.3 meters)
  - 3M™ Matting Edging - Medium Profile
  - 3M™ Matting Adhesive (one 3-ounce tube of adhesive will apply approximately 15 linear feet of edging.)
- Before applying edging ensure that matting and edging are relaxed and not stretched. Unroll matting and edging and allow to lie undisturbed for 24 hours at room temperature. Do not stretch or pull on matting when applying edging.
  - Recommended maximum edge length is 12 feet (4 m).
1. Arrange mat on floor so that the sides to be edged are straight. Trim edges with a utility knife (not scissors) and a straight edge if necessary (see Custom Cutting).
  2. Cut a piece of edging the same length as the edge of mat.
  3. Place edging flat on the floor, grooved side up.
  4. Apply two beads of adhesive liberally to the top of the edging.
  5. Place edge of mat on top of edging groove containing adhesive. Gently work mat snugly into the corner of edging groove to ensure a good fit.
  6. Place a weight, such as a board, along the full length of edging to maintain pressure on the bond. Allow to dry undisturbed for at least 8 hours before placing it into service.